

TECHNICAL SPECIFICATIONS

POLYANE SBE Vert/Blanc

250µm



Specifications		Values	According to
Colour		Green / White	
Particularities		Cattle Shed **	
Thickness	on average	+/- 5 %	NF EN 13 206
	specific	-15%	NF EN 13 206
Width	< 7250	+/- 2 %	ISO 4592
	≥ 7250	-0 +4 %	ISO 4592
Elongation at break (machine)		≥ 450 %	ISO 527-3
Tensile stress at break (machine)		≥ 21 Mpa	ISO 527-3
Elongation at break (cross)		≥ 500 %	ISO 527-3
Tensile stress at break (cross)		> 18 Mpa	ISO 527-3
Creep		≤ 20 %	NF EN 13206
Dart drop test on full film		≥ 500 gr	ISO 7765-1
Tear resistance Elmendorf		≥ 1000 cN	ISO 6383-2
Global light transmission		< 1 X 10 ⁻²	Norme interne
marking		SBE	
Specific laying way		Without	
Length		Meter Print	

The technical data are given as a guide only and can be altered at any time without prior notification.

Réf SBE V-B GB - 27/07/2016

(**) Film guaranteed only for Cattle Shed application. For any other use, please contact us.



AGRIPOLYANE
 Z.I du Clos Marquet - B.P. 188 - 42408 SAINT CHAMOND - France
 Tél : 33 (0)4 77 31 10 00 - Fax : 33 (0)4 77 31 10 75